

FLEETCRYL 2K
FAST HARDENER

PRODUCT CODE: 472199

(Page 1 of 1)

TYPE

- Aliphatic Isocyanate – 2K Hardener
- For use with 2K Enamels and Primers

TECHNICAL DATA

Colour	-	Water white	
S.G. Mixed	-	0,94	
Mixing ratio	-	1:4 with Primer	1:2 with Enamel by volume
Volume solids	-	32 +/-1%	
Pot life	-	6 hours @ 25°C	
Thinners	-	Fleetcryl 2K Thinners	
Drying time	-	Touch dry	: 30 minutes
		Hard to sand	: 2 hours
		Hard to overcoat	: 3 hours

METHOD OF APPLICATION

- Conventional spray.

The technical data furnished is given to the best of our knowledge based on controlled laboratory tests under ideal application conditions. No guarantee of any performance characteristic is therefore given or implied and we do not hold ourselves responsible for any consequential damage of whatsoever nature that may arise from use of our products. In the event of a proven product fault our liability will be limited to the replacement of the product only. It is the user's responsibility to confirm the currency of product data sheets.

FOR FURTHER INFORMATION PLEASE CONTACT: (TOLL FREE) 0800 222 423

Website: www.dekro.co.za e-mail: info@dekro.co.za