

MS PRIMER

PRODUCT CODE: 478201

(Page 1 of 1)

TYPE :

- Polyester / Isocyanate Filler Primer for use as a high build coating on suitably prepared surfaces.

TECHNICAL DATA :

Colour	-	Cream
SG Mixed	-	1.35
Mixing Ratio	-	4 : 1 by volume
Hardener	-	Fleetcryl Fast Hardener (Code 472199)
Volume Solids	-	42%
Pot Life	-	6 hours @ 25°C
Coverage	-	6m ² @ 40μ DFT
Thinners	-	Fleetcryl 2K Thinners
Drying Time	-	Touch Dry : 30 minutes
		Hard to sand : 2 hours
		Hard to overcoat : 3 hours

METHOD OF APPLICATION :

- Conventional spray.
- Mix 4 : 1 : 1 (Base / Hardener / Thinners)

The technical data furnished is given to the best of our knowledge based on ideal application conditions. No guarantee of any performance characteristic is therefore given or implied and we do not hold ourselves responsible for any consequential damage of whatsoever nature that may arise from use of our products. In the event of a proven product fault our liability will be limited to the replacement of the product only. It is the users responsibility to confirm the currency of product data sheets.