



PAINTER'S PAL GARAGE FLOOR PAINT

Page 1 of 3

CODE: 10908* series

REVISION: 02

DATE: 06 January 2021

GENERAL DESCRIPTION

A ready to use quick-drying Water Based Single Pack Satin/Matt enamel, designed for application to various substrates, (new and old), based on a multi-phase, pure acrylic dispersion.

USES AND PROPERTIES

Designed to give a hard-wearing Satin/Matt coating over new or previously painted surfaces. Based on alkali resistant pigments and binder.
Hard-wearing and easy to clean.
Easy repaintable at any stage of life when re-coating becomes necessary.
Prevent disintegration of cement based floors.
Weather Resistant

TECHNICAL DATA

Binder Type	:	Acrylic coating.
Hard Dry	:	6 hours (at 23°C and 50% humidity)
Touch Dry	:	<30 minutes (at 23°C and 50% humidity)
Drying Process	:	Solvent evaporation /coalescing
Over coating	:	6-8 hours
Viscosity	:	80 – 90ku
Specific Gravity	:	1,205 ±0,05kg/ltr
Non Volatile Content	:	Mass: 45%±3%
Volume	:	32%±5%
Gloss	:	Satin/Matt
Coverage	:	8m ² /ltr for 40µ Dry Film Thickness
Flash Point	:	Over 21°C
Application Temp	:	>4°C <40°C
Colour Range	:	Various
Cleaning Equipment With	:	Water
Pack Sizes	:	5 litre, 20 litre

Coverage/spreading rate of **Painter's Pal Garage Floor Paint** depends largely on the condition and porosity of the substrate being painted and manner in which the product is applied.



PAINTER'S PAL GARAGE FLOOR PAINT

Page 2 of 3

SURFACE PREPARATION

New or old concrete floors must be clean from all contaminants.
Smooth surfaces should be etched with Dekro acid etching solution to create a key.
Wash off with water to remove all traces of acid and allow to dry thoroughly

APPLICATION

Correct surface preparation is essential for good product performance and all surfaces should be prepared as per the standard Painter's Pal Preparation Specifications. Copies of these are available on request from your Painter's Pal Paints Outlet or can be downloaded from our website –www.painterspals.co.za.

Do not apply when ambient temperatures are $<4^{\circ}\text{C}$ or $>40^{\circ}\text{C}$. After correct surface preparation, stir thoroughly and apply a minimum of 2 coats of **Painter's Pal Garage Floor Paint** by brush, roller or spray at the specified spread rate. Allow to dry between coats as per technical data.

SAFETY INSTRUCTIONS

Always keep out of reach of children and animals.
Wear a suitable dust mask and goggles when preparing surfaces.
Ensure good ventilation during application and drying.
If accidental contact with skin, wash immediately with soap and water or a recognised skin cleaner.
If accidental contact with eyes, rinse immediately with plenty of water and seek medical advice.
Harmful if swallowed. Seek medical attention and do not induce vomiting.

GENERAL

Different surfaces and environmental conditions require specific painting systems to produce the best possible results.

It is therefore recommended that you contact a Dekro Sales representative for advice on all your painting requirements whenever possible.



PAINTER'S PAL GARAGE FLOOR PAINT

Page 3 of 3

PREVENTING PROBLEMS AND GENERAL INFORMATION

IMPORTANT: Walls (cement plaster, concrete or masonry) must be dry before painting and should not exceed a moisture content of 14% as measured with a Protimeter Surveymaster Moisture Meter or equal. The ambient temperature must be between 4°C and 40°C and humidity between 10% and 85%.

Excessive application thickness and/or rapid drying could lead to mud cracking.

Avoid applying under adverse weather conditions as this could result in poor product performance.

Excessively friable surfaces should be cleaned down prior to primer application.

CLEANING, STORAGE AND DISPOSAL

Remove as much paint as possible from application equipment and wash immediately after use with mineral turpentine. Close containers tightly after use and store in a cool well-ventilated area. Do not empty contents or wash into drains or water courses.

When disposing please follow local authorities' regulations and recycle the container after use. Avoid storing in direct sunlight and heat.

The technical data furnished is given to the best of our knowledge based on controlled laboratory tests under ideal application conditions. No guarantee of any performance characteristic is therefore given or implied and we do not hold ourselves responsible for any consequential damage of whatsoever nature that may arise from use of our products. In the event of a proven product fault our liability will be limited to the replacement of the product only. It is the user's responsibility to confirm the currency of product data sheets.