

DRUIWEBAK PAINT

CODE: 653001

REVISION: 02

DATE: 06 August 2024

GENERAL DESCRIPTION

Druwebak Paint is an acrylic/chlorinated rubber paint offering excellent resistance to weathering and abrasion. This product is tested and certified for indirect and occasional contact with food according to American Regulation FDA 21 CFR 175.300.

USES AND PROPERTIES

Designed specifically for coating metal grape trailers used when harvesting grapes.
Excellent weather and chemical resistance.
Excellent resistance to water.
Good hardness.

TECHNICAL DATA

Binder Type	:	Acrylic/Chlorinated Rubber
Drying Time	Surface Dry	: <2 hours (at 23°C and 50% humidity)
	Hard Dry	: <8 hours (at 23°C and 50% humidity)
Drying Process	:	Solvent evaporation
Overcoating	:	>2 hours
Viscosity	:	70 - 74KU
Specific Gravity	:	1,16 ±0,025kg/litre
Mass Non-Volatile Content	:	49% ±3%
Volume Solids	:	32% ±3%
60° Gloss	:	>50%
Coverage	:	8 - 10m ² /litre
Dry Film Thickness	:	35 microns @ 9m ² /litre
Thin & Clean Equipment With	:	Dekro Spraying Enamel Thinners
Colour Range	:	White
Pack Sizes	:	1 litre, 5 litre

Coverage/spreading rate of **Druwebak Paint** depends largely on the condition and porosity of the substrate being painted and the manner in which the product is applied.

APPLICATION

Ready for use with brush, roller and spray.

Previously painted surfaces

The surface must be sound, well abraded, clean and free of rust. A test patch should be applied before painting the whole area.

DRUIWEBAK PAINT

New surfaces

- Metal-Ferrous : The surfaces must be clean, rust-free and well abraded. Apply one coat of Dekro Vasbyt Single Pack Metal Etch Primer.
- Galvanised Iron : Clean to a water break-free surface with Dekro Galv-Etch and then rinse well with water. Prime with Dekro Vasbyt Single Pack Metal Etch Primer.

Correct surface preparation is essential for good product performance and all surfaces should be prepared as per the standard Dekro Preparation Specifications. Copies of these are available on request from Dekro Paints or can be downloaded from our website – www.dekro.co.za.

SAFETY INSTRUCTIONS

- Always keep out of reach of children and animals.
Wear a suitable dust mask and goggles when preparing surfaces.
Ensure good ventilation during application and drying.
If accidental contact with skin, wash immediately with soap and water or a recognised skin cleaner.
If accidental contact with eyes, rinse immediately with plenty of water and seek medical advice.
Harmful if swallowed. Seek medical attention and do not induce vomiting.

GENERAL

Different surfaces and environmental conditions require specific painting systems to produce the best possible results.
It is therefore recommended that you contact a Dekro Sales representative for advice on all your painting requirements whenever possible.

PREVENTING PROBLEMS AND GENERAL INFORMATION

- The ambient temperature must be between 4°C and 40°C and humidity between 10% and 85%.
The steel temperature must be a minimum of 3°C above dew point, measured in the vicinity of the substrate being painted.
Excessive application thickness and/or rapid drying could lead to mud cracking.
Avoid applying under adverse weather conditions as this could result in poor product performance.
Do not attempt touch ups, but redo complete panels.
Excessively friable surfaces should be cleaned down prior to primer application.
To ensure consistent appearance ensure that the batch numbers on all containers used are the same.
Where batch numbers on containers differ, intermix containers before use.

DANGER

Highly Flammable liquid and vapor. May cause serious eye irritation. May cause drowsiness or dizziness. Repeated exposure may cause skin dryness and cracking.

PREVENTION:

Keep away from heat, sparks and open flames. No smoking. Keep container tightly closed. Ground/bond container and receiving equipment. Use explosion-proof electrical equipment and non-sparking tools. Take precautionary measures against static discharge. Avoid breathing vapors. Use only outdoors or in a well ventilated area. Wear eye protection

RESPONSE:

If on skin: Take off immediately contaminated clothing. Rinse skin with water.
If inhaled: Remove person to fresh air and keep comfortable for breathing. Call a doctor if you feel unwell.
If in eyes: Rinse cautiously with water for several minutes. Remove contact lenses if present and easy to do. Continue rinsing if eye irritation persists: Get medical attention.
In case of fire: use water spray, alcohol resistant foam, dry chemical or carbon dioxide for extinction.

STORAGE:

Store locked up, in a cool, well ventilated place.

DISPOSAL:

Dispose of contents /containers in accordance with local regulations

PLEASE REFER TO MATERIAL SAFETY DATA SHEET FOR ANY PRODUCT UPDATES

COMPLIES WITH THE SOUTH AFRICAN LEGAL LEAD LIMIT OF 90PPM OR LESS



DRUIWEBAK PAINT

CLEANING, STORAGE AND DISPOSAL

Remove as much paint as possible from application equipment and wash immediately after use with Dekro Spraying Enamel Thinners.

Close containers tightly after use and store in a cool well-ventilated area.

Do not empty contents or wash into drains or water courses.

When disposing please follow local authorities' regulations and recycle the container after use.

Avoid storing in direct sunlight and heat.

Technical Data Sheet



DEKRO
IS THE ARCHITECTS CHOICE

The technical data furnished is given to the best of our knowledge based on controlled laboratory tests under ideal application conditions. No guarantee of any performance characteristic is therefore given or implied and we do not hold ourselves responsible for any consequential damage of whatsoever nature that may arise from use of our products. In the event of a proven product fault our liability will be limited to the replacement of the product only. It is the user's responsibility to confirm the currency of product data sheets.