BITUMINOUS PAINT BLACK

CODE: 164003 REVISION: 03 DATE: 21 August 2025

GENERAL DESCRIPTION

An economical black bitumen coating for metal, brick, fibre cement and asbestos surfaces.

USES AND PROPERTIES

Recommended for the sealing of fibre cement gutters and brickwork prior to the application of a finishing coat of Bituminous Aluminium. It has good waterproofing properties.
Low cost, high solid content.
Acceptable glossy, black finish.

TECHNICAL DATA

Binder Type		:	Blend of bituminous resins
Drying Time	Surface Dry	:	2 - 4 hours (at 23°C and 50% relative humidity)
	Hard Dry	:	6 - 8 hours (at 23°C and 50% relative humidity)
Drying Process		:	Solvent evaporation
Overcoating		:	>8 hours
Viscosity		:	110 - 120KU
Specific Gravity		:	1,32 ±0,025kg/litre
Mass Non-Volatile Content		:	86% ±3%
Volume Solids		:	77% ±3%
Gloss		:	Glossy
Coverage		:	±8m²/litre
Dry Film Thickness		:	96 microns @ 8m²/litre
Colour Range		:	Black
Clean Equipment With		:	Mineral Turpentine
Pack Sizes		:	5 litre, 20 litre

Technical Data Sheet

Coverage/spreading rate of **Bituminous Paint Black** depends largely on the condition and porosity of the substrate being painted and the manner in which the product is applied.

APPLICATION

Correct surface preparation is essential for good product performance and all surfaces should be prepared as per the standard Dekro Preparation Specifications. Copies of these are available on request from Dekro Paints or can be downloaded from our website –www.dekro.co.za.

This product does not require elaborate surface preparation, except that surfaces must be clean and dry before application. When recoating, do not work the brush or roller too much over the same area as this product is easily re-dissolved.
To seal absorbent surfaces, apply one coat.
For general maintenance apply one coat.

BITUMINOUS PAINT BLACK

SAFETY INSTRUCTIONS

Always keep out of reach of children and animals.
Wear a suitable dust mask and goggles when preparing surfaces.
Ensure good ventilation during application and drying.
If accidental contact with skin, wash immediately with soap and water or a recognised skin cleaner.
If accidental contact with eyes, rinse immediately with plenty of water and seek medical advice.
Harmful if swallowed. Seek medical attention and do not induce vomiting.

GENERAL

Different surfaces and environmental conditions require specific painting systems to produce the best possible results.
It is therefore recommended that you contact a Dekro Sales representative for advice on all your painting requirements whenever possible.

PREVENTING PROBLEMS AND GENERAL INFORMATION

Do not overcoat with decorative top coats as bleeding will occur.
All solvents will soften the film.
Should not be exposed to direct sunlight as this can cause premature breakdown of the film.
Dry **Bituminous Paint Black** can be removed with Mineral Turpentine.

IMPORTANT: Walls (cement plaster, concrete or masonry) must be dry before painting and should not exceed a moisture content of 10% as measured with a Protimeter Surveymaster Moisture Meter or equal.
The ambient temperature must be between 4ºC and 40ºC and humidity between 10% and 85%.
Excessive application thickness and/or rapid drying could lead to mud cracking.
Avoid applying under adverse weather conditions as this could result in poor product performance.
Excessively friable surfaces should be cleaned down prior to primer application.

CLEANING, STORAGE AND DISPOSAL

Remove as much paint as possible from application equipment and wash immediately after use with Mineral Turpentine.
Close containers tightly after use and store in a cool well-ventilated area.
Do not empty contents or wash into drains or water courses.
When disposing please follow local authorities' regulations and recycle the container after use.
Avoid storing in direct sunlight and heat.

Technical Data Sheet

APPLICATIONS FOR AFRICA™

DEKRO
IS THE ARCHITECTS CHOICE

The technical data furnished is given to the best of our knowledge based on controlled laboratory tests under ideal application conditions. No guarantee of any performance characteristic is therefore given or implied and we do not hold ourselves responsible for any consequential damage of whatsoever nature that may arise from use of our products. In the event of a proven product fault our liability will be limited to the replacement of the product only. It is the user's responsibility to confirm the currency of product data sheets.