PAINTER'S PAL
PAINT & ACCESSORIES

BRAAI PAINT



600°C

HIGH HEAT ANTI CORROSION
WATERBASED COATING



PAINTER'S PAL BRAAI PAINT

Anti-Corrosion Coating For
Ovens, Oven Inserts



PAINTER'S PAL BRAAI PAINT

Anti-Corrosion Coating For
Braais and Barbecues





USES AND PROPERTIES:
Painter's Pal Braai Paint is anti-corrosion coating for mufflers, ovens, chimneys, oven inserts, barbeques and electric and gas heaters - heat-resistant decorative coatings. Painter's Pal Braai Paint is high-temperature anti-corrosion that can withstand non-continuous heat resistance of up to 600 °C

TECHNICAL DATA:

Binder Type	Modified Acrylic Emulsion, Non Toxic
Drying Time	Surface Dry: <1 hours (at 23°C and 50% humidity) Hard Dry: <4 hours (at 23°C and 50% humidity)
Drying Process	Water evaporation followed by heat cure
Over coating	>4 hours
Viscosity	95 - 100 KU
Specific Gravity	1,05 ±0,05kg/litre
Non-Volatile Content	54% ±3%
Volume	52% ±3%
Gloss	Satin Sheen
Coverage	6 - 7m²/litre
Dry Film Thickness	25 microns @ 7m²/litre
Thin With	Water
Clean Equipment With	Water
Colour Range	Black
Pack Sizes	Pack Sizes : 1ltr

Coverage/spreading rate of Painter's Pal Braai Paint depends largely on the condition and porosity of the substrate being painted and manner in which the product is applied.

SCAN FOR

TECHNICAL DATA SHEET

BRAAI PAINT

BRAAI PAINT- COMMON PROBLEMS AND SOLUTIONS

PAINT ADHESION ISSUES
POOR PREPARATION AND CLEANING OF SURFACE. REMOVE BACK TO SUBSTRATE AND REPEAT PROCESS

CORROSION RETURN
RUST NOT PROPERLY REMOVED. REMOVE ALL RUST BACK TO CLEAN METAL AND REPEAT PROCESS

PAINT DELAMINATION
POOR PREPARATION. POOR SURFACE CONDITIONS. REMOVE PAINT BACK TO SUITABLE SUBSTRATE AND REPEAT PROCESS

Correct surface preparation is essential for good product performance and all surfaces should be prepared as per the standard Dekro Preparation Specifications.
Copies of these are available on request from your Dekro Paints or can be downloaded from our website –www.dekro.co.za.
Do not apply when ambient temperatures are <4°C or >40°C. After correct surface preparation, then stir thoroughly
and apply a minimum of 2 coats of Painter's Pal Braai Paint by brush, roller or spray at the specified spread rate. Allow to dry before over coating as per technical data.

DEKRO PAINTS 24 FABRIEK STREET KUILS RIVER
INFO@DEKRO.CO.ZA WWW.DEKRO.CO.ZA 0800 222 423 (TOLL FREE)

APPLICATIONS FOR AFRICA®