DEKRO PAINTS

DRUIWEBAK



GRAPE TRAILER AND FARM IMPLEMENT PAINT









DRUIWEBAK

USES AND PROPERTIES:
An acrylic/chlorinated rubber paint offering excellent resistance to weathering and abrasion. This product is tested and certified for indirect and occasional contact with food according to American Regulation FDA 21 CFR 175.300.

TECHNICAL DATA:

Binder Type	**Acrylic/Chlorinated Rubber**
Drying Time	**Surface Dry: <2 hours (at 23°C and 50% humidity)** **Hard Dry: <8 hours (at 23°C and 50% humidity)**
Drying Process	**Solvent evaporation**
Over coating	**>2 hours**
Viscosity	**70 - 74 KU**
Specific Gravity	**1,16 ±0,025kg/litre**
Non-Volatile Content	**49% ±3%**
Volume	**32% ±3%**
Gloss	**>50%**
Coverage	**8 - 10m²/litre**
Dry Film Thickness	**35 microns @ 9m²/litre**
Thin With	**Dekro Spraying Enamel Thinner**
Clean Equipment With	**Dekro Spraying Enamel Thinners**
Colour Range	**White, Grey and Green Mist (Colours in minimum 200L)**
Pack Sizes	**Pack Sizes : 1ltr, 5ltr**

SCAN FOR

TECHNICAL DATA SHEET

Coverage/spreading rate of Druiwebak depends largely on the condition and porosity of the substrate being painted and manner in which the product is applied.

Correct surface preparation is essential for good product performance and all surfaces should be prepared as per the standard Dekro Preparation Specifications. Copies of these are available on request from your Dekro Paints or can be downloaded from our website –www.dekro.co.za. Do not apply when ambient temperatures are <4°C or >40°C. After correct surface preparation, prime with the recommended primer, then stir thoroughly and apply a minimum of 2 coats of Druiwebak Paint by brush, roller or spray at the specified spread rate. Allow to dry before over coating as per technical data.

DRUIWEBAK- COMMON PROBLEMS AND SOLUTIONS

PAINT ADHESION ISSUES

INCORRECT PRIMER USED. REMOVE BACK TO SUITABLE SUBSTRATE AND REPEAT PROCESS

SPIDER WEBBING AND OR BUBBLES FORMING

INCORRECT THINNERS USED
FLAT SURFACE WITH SANDPAPER AND RE-APPLY WITH CORRECT THINNERS

PAINT DELAMINATION

POOR PREPARATION. POOR SURFACE CONDITIONS. REMOVE PAINT BACK TO SUITABLE SUBSTRATE AND REPEAT PROCESS

DEKRO PAINTS 24 FABRIEK STREET KUILS RIVER
INFO@DEKRO.CO.ZA WWW.DEKRO.CO.ZA 0800 222 423 (TOLL FREE)

APPLICATIONS FOR AFRICA®