DEKRO PAINTS

QD ENAMEL TRUCK AND TRACTOR





QUICK DRYING GLOSS ENAMEL COATING









QD ENAMEL

USES AND PROPERTIES:
Superb appearance with a high gloss good build and opacity. Excellent durability and gloss retention. Recommended for the protection of exterior metal surfaces where a glossy durable finish is required. Appropriate primers must always be used, particularly on bare steel surfaces.

TECHNICAL DATA:

Binder Type	Alkyd Resin
Drying Time	<30 minutes (at 23°C and 50% humidity)) <2 hours (at 23°C and 50% humidity)
Drying Process	Solvent evaporation and cross linking
Over coating	>2 hours, <12 hours
Viscosity	100 - 110 seconds Ford Cup No. 4
Specific Gravity	0,88 - 1,00 ±0,025kg/litre (depending on colour)
Non-Volatile Content	25 - 50% ±3% (depending on colour)
Volume	20 - 25% ±3% (depending on colour)
Gloss	High gloss >75%
Coverage	6m-8m²/ltr
Dry Film Thickness	37 microns @ 6m²/litre
Thin With	Dekro Spraying Enamel Thinners
Clean Equipment With	Dekro Spraying Enamel Thinners
Colour Range	As per Standard Colour Card (Colours in minimum 200L)
Pack Sizes	1ltr, 5ltr

SCAN FOR

TECHNICAL DATA SHEET

Coverage/spreading rate of QD Enamel Truck & Tractor depends largely on the condition and porosity of the substrate being painted and manner in which the product is applied.

Correct surface preparation is essential for good product performance and all surfaces should be prepared as per the standard Dekro Preparation Specifications.
Copies of these are available on request from your Dekro Paints or can be downloaded from our website –www.dekro.co.za.
Do not apply when ambient temperatures are <4°C or >40°C. After correct surface preparation, prime with the recommended primer, then stir thoroughly and apply a minimum of 2 coats of QD Enamel Truck & Tractor by brush, roller or spray at the specified spread rate. Allow to dry before over coating as per technical data.

QD ENAMEL TRUCK AND TRACTOR - COMMON PROBLEMS AND SOLUTIONS

PAINT ADHESION ISSUES
INCORRECT PRIMER USED. REMOVE BACK TO SUITABLE SUBSTRATE AND REPEAT PROCESS

SPIDER WEBBING AND OR BUBBLES FORMING
INCORRECT THINNERS USED
FLAT SURFACE WITH SANDPAPER AND RE-APPLY WITH CORRECT THINNERS

PAINT DELAMINATION
POOR PREPARATION. POOR SURFACE CONDITIONS. REMOVE PAINT BACK TO SUITABLE SUBSTRATE AND REPEAT PROCESS

DEKRO PAINTS 24 FABRIEK STREET KUILS RIVER
INFO@DEKRO.CO.ZA WWW.DEKRO.CO.ZA 0800 222 423 (TOLL FREE)

APPLICATIONS FOR AFRICA®