DEKRO PAINTS

RAINPROOF



WATERBASED LIQUID PLASTIC COATING FOR ROOFS AND WALLS



Waterbased Liquid Plastic Coating
For Cement Roof Ridge Tiles



Waterbased Liquid Plastic
For Exterior Walls





RAINPROOF

USES AND PROPERTIES:
Dekro Rainproof is a Modified flexible acrylic emulsion with a slight sheen for waterproofing of roofs, parapets and wall surfaces.

TECHNICAL DATA:

Binder Type	**PU Modified Acrylic Emulsion**
Drying Time	**Surface Dry: <1 hours (at 23°C and 50% humidity)** **Hard Dry : <8 hours (at 23°C and 50% humidity)**
Drying Process	**Water evaporation followed by coalescent**
Over coating	**>12 hours**
Viscosity	**120 - 125KU**
Specific Gravity	**1,31 ±0,05kg/litre**
Non-Volatile Content	**55% ±3%**
Volume	**41% ±3%**
Gloss	**Satin Sheen**
Coverage	**1-4m²/ltr**
Dry Film Thickness	**102 microns @ 4m²/litre**
Colour Range	**White, Black, Red Oxide, Chrome Oxide, Grey & Pastel Colours**
Pack Sizes	**Pack Sizes : 1ltr, 5ltr, 20ltr**

SCAN FOR

TECHNICAL DATA SHEET

Coverage/spreading rate of Dekro Non Drip Enamel depends largely on the condition and porosity of the substrate being painted and manner in which the product is applied.

Correct surface preparation is essential for good product performance and all surfaces should be prepared as per the standard Dekro Preparation Specifications.
Copies of these are available on request from your Dekro Paints or can be downloaded from our website –www.dekro.co.za.
Do not apply when ambient temperatures are <4°C or >40°C. After correct surface preparation, prime with the recommended primer, then stir thoroughly and apply a minimum of 1 coat of Vasbyt Single Pack Metal Etch Primer by brush, roller or spray at the specified spread rate. Allow to dry before over coating as per technical data.

RAINPROOF - COMMON PROBLEMS AND SOLUTIONS

PAINT ADHESION ISSUES

INCORRECT PREPERATION AND CLEANING. REMOVE BACK TO SUITABLE SUBSTRATE AND REPEAT PROCESS. USE SUITABLE PRIMERS.

POOR FLOW AND BUBBLES FORMING

SURFACE TEMPERATURE TOO COLD AND OR POOR SURFACE PREPARATION. SAND FLAT AND REPEAT PROCESS WHEN CONDITIONS ARE SUITED.

PAINT DELAMINATION

POOR PREPARATION. POOR SURFACE CONDITIONS. REMOVE PAINT BACK TO SUITABLE SUBSTRATE AND REPEAT PROCESS. USE SUITABLE PRIMERS.

DEKRO PAINTS 24 FABRIEK STREET KUILS RIVER
INFO@DEKRO.CO.ZA WWW.DEKRO.CO.ZA 0800 222 423 (TOLL FREE)

APPLICATIONS FOR AFRICA®