PAINTER'S PAL
PAINT & ACCESSORIES

SKIM AND FILL



READY-TO-USE FILLER AND SKIMMING COMPOUND

PAINTER'S PAL SKIM AND FILL



Ready to Use Skimming Plaster
For Interior Wall Surfaces

PAINTER'S PAL SIM AND FILL



Ready to Use Skimming Plaster
For Interior Ceilings



PAINTER'S PAL SKIM AND FILL

Ready to Use Filler
For interior Wall Cracks



PAINTER'S PAL SKIM AND FILL

Ready to Use For
Interior Tape and Joining

SKIM AND FILL

USES AND PROPERTIES:
PAINTER'S PAL SKIM-AND-FILL is an environmentally friendly, multipurpose, ready-mixed filler that dries to a matt finish. This is a scraper coat for plastered walls to fill in surface imperfections prior to painting. Can be sanded once fully dried. The product conforms to the GBCSA environmental requirements and EU 2010 targets.

TECHNICAL DATA:

Binder Type	Acrylic
Drying Time	Surface Dry: <1 hour (at 23°C and 50% humidity) Hard Dry: <4hours (at 23°C and 50% humidity)
Drying Process	Water Evaporation / Coalescing
Over coating	>6 hours
Viscosity	130- 135 PP
Specific Gravity	1,75 ±0,05kg/litre
Pigment Volume Content	1-2m2/kg
Volume and Mass	50% ±3% and 70% ±3%
Gloss	Satin Sheen
Coverage	1m²/kg as skim coat 40 microns @ 8m²/litre
Dry Film Thickness	Water
Clean Equipment With	White
Colour Range	Pack Sizes : 8kg and 32kg
Pack Sizes	

SCAN FOR

TECHNICAL DATA SHEET

Coverage/spreading rate of Painter's Pal Skim and Fill depends largely on the condition and porosity of the substrate being painted and manner in which the product is applied.

Correct surface preparation is essential for good product performance and all surfaces should be prepared as per the standard Dekro Preparation Specifications.
Copies of these are available on request from your Dekro Paints or can be downloaded from our website –www.dekro.co.za.
Do not apply when ambient temperatures are <4°C or >40°C. After correct surface preparation, then stir thoroughly
and apply a minimum of 2 coats of Painter's Pal Braai Paint by brush, roller or spray at the specified spread rate. Allow to dry before over coating as per technical data.

SKIM AND FILL- COMMON PROBLEMS AND SOLUTIONS

PAINT ADHESION ISSUES

THIS PRODUCT IS NOT SUITABLE FOR EXTERIOR USE. ALL CRACKS >0.5MM MUST BE PREPARED IN THE RECOMMENDED MANNER. PAINTER'S PAL SKIM- AND-FILL MAY NOT COVER THEM EFFECTIVELY

OVERCOATING TIME

THIS IS LARGELY DEPENDENT ON FILM THICKNESS AND AMBIENT TEMPERATURE. UNDER IDEAL CONDITIONS WE RECOMMEND A MINIMUM OF 6 HOURS BEFORE SANDING AND OVER COATING, BUT WHEN IN DOUBT IT IS BEST TO LEAVE OVERNIGHT BEFORE SANDING AND OVER COATING

DEKRO PAINTS 24 FABRIEK STREET KUILS RIVER
INFO@DEKRO.CO.ZA WWW.DEKRO.CO.ZA 0800 222 423 (TOLL FREE)

APPLICATIONS FOR AFRICA®