
DEKRO PAINTS

TRAFFIC PAINT





ROADMARKING AND TRAFFIC PAINT



TRAFFIC PAINT

Roadmarking and Traffic Paint
For Municipal and National Roads



TRAFFIC PAINT

Roadmarking and Traffic Paint
For Signage and Demarcations





TRAFFIC PAINT

USES AND PROPERTIES:
SDirect application to all types of bituminous and dry concrete road surfaces. Also suitable for line marking in warehouses and garages. An ideal paint for signwriting on roads, garages and factory floors. Not recommended as a decorative coating.

TECHNICAL DATA:

Binder Type	**Alkyd Resin**
Drying Time	**Surface Dry: <15 minutes (at 23°C and 50% humidity)** **Hard Dry : <30 minutes (at 23°C and 50% humidity)**
Drying Process	**Solvent evaporation and cross linking**
Viscosity	**90 - 95KU**
Specific Gravity	**1,29 - 1,38 ±0,05kg/litre (depending on colour)**
Non-Volatile Content	**61 - 66% ±3% (depending on colour)**
Volume	**39 - 46% ±3% (depending on colour)**
Coverage	**4 - 6m²/ltr for**
Dry Film Thickness	**78 - 92 microns @ 5m²/litre**
Thin and Clean Equipment With	**Dekro Spraying Enamel Thinners (Product ready for use so no thinning required)**
Colour Range	**Standard Colour Chart**
Pack Sizes	**Pack Sizes : 1ltr, 5ltr, 20ltr, 200ltr**

Coverage/spreading rate of Dekro Traffic Paint depends largely on the condition and porosity of the substrate being painted and manner in which the product is applied.

SCAN FOR

TECHNICAL DATA SHEET

TRAFFIC PAINT - COMMON PROBLEMS AND SOLUTIONS

PAINT ADHESION ISSUES

INCORRECT PREPERATION AND CLEANING. REMOVE BACK TO SUITABLE SUBSTRATE AND REPEAT PROCESS

SPIDER WEBBING AND OR BUBBLES FORMING

INCORRECT THINNERS USED
FLAT SURFACE WITH SANDPAPER AND RE-APPLY WITH CORRECT THINNERS

PAINT DELAMINATION

POOR PREPARATION. POOR SURFACE CONDITIONS. REMOVE PAINT BACK TO SUITABLE SUBSTRATE AND REPEAT PROCESS

Correct surface preparation is essential for good product performance and all surfaces should be prepared as per the standard Dekro Preparation Specifications.
Copies of these are available on request from your Dekro Paints or can be downloaded from our website –www.dekro.co.za.
Do not apply when ambient temperatures are <4°C or >40°C. After correct surface preparation, prime with the recommended primer, then stir thoroughly and apply a minimum of 1 coat of Vasbyt Single Pack Metal Etch Primer by brush, roller or spray at the specified spread rate. Allow to dry before over coating as per technical data.

DEKRO PAINTS 24 FABRIEK STREET KUILS RIVER
INFO@DEKRO.CO.ZA WWW.DEKRO.CO.ZA 0800 222 423 (TOLL FREE)

APPLICATIONS FOR AFRICA